



Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Technical Data

June, 2001

Product Description

3M™ Scotch-Weld™ Low-Odor Acrylic Adhesives are two-part, 1:1 mix ratio, toughened structural adhesives with less odor than most acrylic adhesives. These adhesives have excellent shear and peel strength along with good impact resistance and durability. They can quickly bond to most metals, ceramics, rubbers, plastics and wood with minimal surface preparation.

Features

- Tough, durable bonds
- Minimal surface prep
- 10 minute time to handling strength
- Bonds stainless steel
- Low-odor acrylic adhesive
- 10 minute worklife
- 1:1 mix ratio
- Excellent shear and peel strength

Typical Uncured Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Property		DP-810	DP-810 Black	DP-810 NS
Color	Base (B) Accelerator (A)	Green White	Black White	Blue/Green White
Lbs./gal.	Base (B) Accelerator (A)	8.7 - 9.1 8.7 - 9.1	8.5 - 8.9 8.6 - 9.0	8.8 - 9.2 8.7 - 9.1
Viscosity (cps)⁽¹⁾	Base (B) Accelerator (A)	18,000 - 22,000 18,000 - 22,000	18,000 - 22,000 17,000 - 21,000	90,000 - 95,000 95,000 - 100,000
Base Resin	Base (B) Accelerator (A)	Acrylic Acrylic	Acrylic Acrylic	Acrylic Acrylic
Mix Ratio	(Volume) (Weight)	1:1 1:1	1:1 1:1	1:1 1:1
Time to Handling Strength (50 psi)		10 minutes	10 minutes	10 minutes
Full Cure @ 73°F (23°C)		8 - 24 hours	8 - 24 hours	8 - 24 hours
Worklife @ 73°F (23°C)		10 minutes	10 minutes	10 minutes

Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Typical Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Overlap Shear Strength⁽²⁾, tested @ 73°F (23°C)

	DP-810	DP-810 Black	DP-810 NS
Substrate	OLS (psi)	OLS (psi)	OLS (psi)
Etched Aluminum	4200 CF	4200 CF	4200 CF
Abraded Aluminum	3900 CF	3750 CF	3850 CF
Bare Aluminum	3800 CF	3850 CF	4100 CF
CRS	3100 CF	3600 CF	3500 CF
Oily CRS	3450 CF	3450 CF	3500 CF
Stainless Steel	3400 CF	3500 CF	3400 CF
Green FRP	3800 CF	3000 CF	1900 CF
Acrylic	1100 SF	550 MM	800 SF
PVC	1000 SF	1000 SF	1000 SF
Polycarbonate	850 MM	500 MM	500 MM
ABS	600 MM	700 MM	650 MM

Overlap Shear Strength psi, tested @ Temperature

Temperature	DP-810	DP-810 Black	DP-810 NS
-20°F (-29°C)	1750 AF/MM	2000 AF/MM	1600 AF
75°F (24°C)	3650 CF	3550 CF	4000 CF
120°F (49°C)	2000 CF	2000 CF	2350 CF
180°F (82°C)	550 CF	500 CF	500 CF

T-Peel Strength (piw)⁽³⁾, tested @ 73°F (23°C)

Substrate	DP-810	DP-810 Black	DP-810 NS
Etched Al	30	20	23

SF = Substrate Failure/Break
 CF = Cohesive Failure
 AF = Adhesive Failure
 MM = Mixed (Mode of AF and CF)

Scotch-Weld™
Low-Odor Acrylic Adhesives
 DP-810 • DP-810 Black • DP-810 NS

Environmental Resistance⁽⁴⁾

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Overlap Shear Strength (psi), tested @ 73°F (23°C)

Condition	Time	DP-810	DP-810 Black	DP-810 NS
Control	14 Days	3750 CF	3750 CF	3800 CF
160°F (71°C)/100% RH	14 Days	1500 MM	1500 MM	1250 AF
160°F (71°C)/Soak	14 Days	1750 MM	1650 MM	1450 AF
20% Bleach	14 Days	3450 CF	3250 CF	3750 CF
IPA	14 Days	3150 CF	3050 CF	3450 CF
50% Antifreeze	14 Days	3850 CF	3900 CF	4000 CF
Gasoline	14 Days	2550 CF	2550 CF	3150 CF
Diesel Fuel	14 Days	4000 CF	3950 CF	4050 CF
Toluene	14 Days	2650 CF	2600 CF	3400 CF
MEK	14 Days	50 CF	75 CF	2100 CF
Acetone	14 Days	75 CF	50 CF	900 CF

CF = Cohesive Failure
 MM = Mixed (Mode of AF and CF)
 AF = Adhesive Failure

Typical Rate of Strength Build-Up

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Overlap Shear Strength (psi), tested @ 73°F (23°C) at various times after bonding.

Condition	DP-810	DP-810 Black	DP-810 NS
10 minutes	50	30	500
20 minutes	1500	1150	1750
1 hour	2250	2200	2850
2 hours	2750	2700	3350
4 hours	2950	2900	3700
8 hours	3350	3200	3850
24 hours	3600	3550	4000

Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Test Methods and Footnotes

- 1) Viscosity obtained by Brookfield, DV-II, #7 Spindle, 20 rpm at 75°F (24°C).
- 2) Overlap Shear Test Method: overlap shear test for adhesion determined in accordance to ASTM D1002-72, sample dimensions were 1" x 4" x 1/8", with a 1/2 square inch area of overlap, bonded to themselves unless otherwise noted, allowed to cure for at least 6 hours at 75°F (24°C) before testing. Data were collected using a Sintech 5GL Mechanical Tester with a 2000# or 5000# load cell. Test rate was 0.1"/minute. Strength determined at 75°F (24°C) unless otherwise noted.
- 3) Peel tests (ASTM D1876-61T) on FPL etched, 0.032" gauge aluminum, with a .017" bondline thickness. Jaw separation rate 20"/min. All bonds were allowed to cure for at least 6 hours at 75°F (24°C) before testing.
- 4) Environmental tests were conducted by immersing bonded coupons prepared in accordance to description in footnote 2.

Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Handling/Curing Information

Directions for use:

Apply adhesive to clean, dry substrates, which are free of paint, oxide films, oils, dust, mold release agents and all other surface contaminants. See the Surface Preparation section for specific substrate preparation method.

50 ml cartridge:

Place Duo-Pak cartridge in 3M™ EPX™ Applicator. Remove cap. Dispense and discard a small amount of adhesive to assure even ratio and free flow. Clear orifice if necessary. Attach mixing nozzle. Apply adhesive to clean surfaces, join parts, secure until adhesive sets [15 minutes @ 70°F (21°C)].

Adhesive will fully cure in 6 hours @ 70°F (21°C). Store unused adhesive at 40°F (4°C) or below.

200/400 ml cartridge

While holding Duo-Pak cartridge in an upright position, remove and discard the insert from the cartridge by unscrewing plastic nut and removing metal washer. Place cartridge in a 1:1 200/400 ml EPX applicator. Dispense and discard a small amount of adhesive to ensure even ratio and free flow. Attach mixing and nozzle and secure with plastic retaining nut. Apply adhesive to clean surfaces, join parts, secure until adhesive sets [15 minutes at 70°F (21°C)]. Adhesive will fully cure in 6 hours @ 70°F (21°C). Store unused adhesive at 40°F (4°C) or below.

Bulk Container Directions:

Follow manufacturer's directions for bulk dispensing equipment.

Clean-up:

Excess adhesive can be removed with solvent such as 3M™ Scotch-Grip™ Solvent No. 3 or equivalent. Edge tack on a finished part or bond line can be removed with isopropyl alcohol*.

***Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

Heat Cure:

Full cure can be attained by raising the bondline temperature to 150°F (66°C) for 10 minutes.

Approximate Coverage – By Size of Container

Bead Size	Linear ft per 50 ml	Linear ft per 200 ml	Linear ft per 400 ml	Linear ft per mixed gallon
1/2"	2.5	10	21	196
3/8"	4.5	18	37	350
1/4"	10.5	41	83	785
1/8"	41.5	165	331	3,130
1/16"	165	656	1,313	12,420

Square ft per 50 ml	Square ft per 200 ml	Square ft per 400 ml	Square ft per mixed gallon
5.2	20.8	41.6	400

Coverage in square feet – (.004" bond line)

Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Surface Preparation

3M™ Scotch-Weld™ Low-Odor Acrylic Adhesives can bond oily metal, plastic and other substrates with very little surface preparation. However, for the most consistent results and environmental resistance, all substrates should be clean, dry and free of paint, oxide films, dust, mold release agents and all other surface contaminants. The amount of surface preparation directly depends on the bond strength and environmental resistance desired by the user.

The following cleaning methods are suggested for common surfaces.

Steel and Aluminum

- 1) Wipe free of dust with oil-free solvent such as acetone or isopropyl alcohol.
- 2) Sandblast or abrade using clean fine grit abrasives (180 grit or finer).
- 3) Wipe again with solvent to remove loose particles.
- 4) If a primer is used, it should be applied within 4 hours after surface preparation. If 3M™ Scotch-Weld™ Structural Adhesive Primer 1945 B/A is used, apply a thin coating (.0005") on the metal surfaces to be bonded, air dry at 75°F (24°C) for 1 hr, then cure for 30 minutes at 180°F (82°C), 5 minutes at 250°F (122°C) or 3 hours at 75°F (24°C).

Note: Aluminum may also be acid etched. Follow the manufacturer's precautions and directions for this procedure.

Plastic/Rubber

- 1) Wipe with isopropyl alcohol.*
- 2) Abrade using fine grit abrasives (180 grit or finer).
- 3) Remove residue by wiping again with isopropyl alcohol.*

Glass

- 1) Solvent wipe surface using acetone.*
- 2) Apply a thin coating (0.0001" or less) of 3M™ Scotch-Weld™ EC-3901 Primer to the glass surfaces to be bonded and allow the primer to dry a minimum of 30 minutes at 75°F (24°C) before bonding for maximum adhesion.
- 3) Remove residue by wiping again with isopropyl alcohol.*

***Note:** When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Storage and Shelf Life

Storage: For maximum shelf life, store Duo-Pak cartridges and bulk containers at 40°F (4°C) or below. Store bulk containers at 40°F (4°C) or below.

Shelf Life: When stored at the recommended temperatures in the original unopened containers, this product has a shelf life of twelve months from date of manufacture.

Scotch-Weld™

Low-Odor Acrylic Adhesives

DP-810 • DP-810 Black • DP-810 NS

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for Health and Safety Information before using the product.

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550. Address correspondence to: 3M Engineered Adhesives Division, 3M Center, Building 220-8E-05, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Important Notice

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M Engineered Adhesives Division product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Limitation of Remedies and Liability

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.



This Engineered Adhesives Division product was manufactured under a 3M quality system registered to ISO 9002 standards.

For Additional Product Safety and Health Information, See Material Safety Data Sheet, or call:



Engineered Adhesives Division

3M Center, Building 220-8E-05
St. Paul, MN 55144-1000
Phone: 1-800-364-3577 or 651/737-6501
www.3m.com/adhesives



Recycled Paper
40% pre-consumer
10% post-consumer

Printed in U.S.A.
©3M 2001 78-6900-9991-2