

3M™ Dissipative Vinyl Three-Layer Mats and Runners Properties

Property	Typical Value
Material	Top and Bottom Layers - Vinyl
Thickness	0.138 in. (3,5 mm)
Hardness	65-70 Shore A
(Surface to Ground)	1×10^7 ohms
(Surface to Surface)	4×10^7 ohms

Tested per ESD Association S4.1 at 72°F, 50RH using 3M 701 Test Kit for Static Control Surfaces (Megohmmeter).