



853 Polyester Tape (Transparent)

Product Data Sheet

Updated : March 1996
Supersedes : October 1993

Product Description A transparent polyester film backing and an exceptionally solvent resistant acrylic adhesive system.

Physical Properties
Not for specification purposes

Adhesive Type	Acrylic	
Backing	0.02mm Polyester film.	
Thickness (ASTM D-3652)	50 µm	
Tape Colour	Transparent	
Shelf Life	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics
Not for specification purposes

Adhesion to Stainless Steel ASTM D-3330	5.2 N/10mm	
Tensile Strength ASTM D-3759	42.1 N/10mm	
Elongation at Break ASTM D-3759	102 %	
Temperature Range Maximum Minimum	175 °C -50 °C	
Water Vapour Transmission Rate	24.8 gms water/m ² /24hrs.	

Date : March 1996
853 Polyester Tape
(Transparent)

Additional Product Information

Adhesive bond will increase to most surfaces upon ageing.

Not recommended to exceed one year under normal storage conditions at 21°C and 50% R.H.

SOLVENT RESISTANCE

**ADHESION TO 24st ALUMINIUM
(applied 72 hrs. before immersion)**

24hrs. immersion distilled water.	3.3 N/10mm
72hrs. immersion lubricating oil. jet engine (MIL-0-6081).	3.3 N/10mm
72hrs. immersion hydraulic oil (MIL-I-0-5606).	3.3 N/10mm
72hrs. immersion hydraulic fluid non-flammable (MIL-F-7083).	3.3 N/10mm
72hrs. immersion non-petroleum base aircraft hydraulic fluid (MIL-H-8446).	3.3 N/10mm
72hrs. immersion jet engine fuel (MIL-F-5624 grade JP4).	3.3 N/10mm
24hrs. immersion aromatic fuel (MIL-H-3136, Type II).	3.3 N/10mm
24hrs. immersion lube oil (MIL-L-7807) at 200°F (93°C).	3.3 N/10mm

Application Techniques

Best results are attained when applied to a clean, dry and non dusty surface above 0°C.

To improve adhesion ensure firm and even application pressure is applied.

Applications

Critical splicing applications.

Solvent resistant masking.

Quality protective laminate.

Tape hinge.

FEATURES

ADVANTAGES

BENEFITS

Polyester backing.

Remains flexible from -50°C to 175°C.

Reduces failure due to embrittlement.

Thermal resistance.

Reduces failure due to film shrinkage and adhesive exposure.

Acrylic adhesive.

Extremely high chemical and solvent resistance.

Protects against failure due to undercutting or adhesive softening.

Firm, long ageing, non-yellowing.

Reduces failure caused by adhesive oozing and loss of tack.

Date : March 1996
853 Polyester Tape
(Transparent)

Specifications

Resistant to penetration (MIL-I-7798A): This criterion to determine its suitability as a dissimilar metal insulator, found that it has excellent insulation properties up to 160°C. This value is probably higher except that this is the maximum limit of the testing equipment.

Printable on the adhesive side and by the "Print Seal" method on the backing side.
NOTE: When laminated to printed No. 852, No. 853 can be qualified to meet requirements on MIL-T-9906A, Amendment I for non-corrosive heat, cold and solvent resistant identification marking tape in aircraft and missiles.

Can be qualified to meet Fed. Spec. L-T-100a, Type I.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



Specialty Tapes & Adhesives

© 3M United Kingdom PLC 1996

3M United Kingdom PLC
3M House,
28 Great Jackson Street,
Manchester,
M15 4PA

Customer Service :
Tel 0161 236 8500
Fax 0161 237 1105

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509